

Industrial Products International Inc.
 Phone: 303-934-2395
 Fax: 303-934-2491
 1655 W Yale Ave
 Englewood, Co 80110-1026



Data Sheet of

CC350

Upper Application limit temperature	1000 °C			
Bulky Density	1040 kg/m³			
Open porosity	58%			
Compression strength	28 MPa			
Flexural strength	13 MPa			
Hardness	70 Shore D			
<u>Shrinkage after 12h</u>				
Length and width 750°C	0.25%			
Thickness 750°C	.80%			
Length and width 1000°C	.30%			
Thickness 1000°C	1.50%			
<u>Thermal Conductivity</u>	(W/m K)			
200°C	0.27			
400°C	0.28			
600°C	0.31			
800°C	0.35			
<u>Chemical composition</u>				
Calcium silicate	95-97%			
(CaO-; MgO-; Al ₂ O ₃ -)silicate	-			
R _x O _x (R=Fe,Ti,K,Na)	1%			
<u>Dimensions</u>				
Standard sizes & tolerances	Length	±2;*0/+50	mm	1,000/1,500/3,000*
(Surface ground on both sides, without trimming)	Width	0/+20	mm	1,250
	Thickness	0/+0.8	mm	12.7/19.1/25.4/31.8/38.1/50.8/76.2/101.6

The information provided in this data sheet does not present guaranteed properties and cannot be used for any warranty claims.